

Discover® SP-D 80™ Method Note

Microwave Digestion of Aluminium

Procedure

Weigh 0.5 g of the sample into the digestion vessel. Add 9 mL HCl and 3 mL DIH_2O . Gently swirl the mixture and wait approximately 15 minutes before capping the vessel.

Notes

HCl should be added slowly and carefully to the sample. Allow any initial reaction to subside before sealing vessel.

Recommended Equipment	Recommended Vessels	Reagents
Discover SP-D 80	80 mL Quartz	HCI DIH ₂ O

Max Sample Weight	Sample Type / Vent Program	Control Type	
0.5 g	Organic	Ramp to Temperature	

Heating Progra	am					
Stage	Temp (°C)	*Ramp (mm:ss)	Hold (mm:ss)	Pressure (psi)	* Power (W)	Stirring
1	200	5:00	5:00	400	300	Med

^{*} Ramp times and power may vary depending on the type and number of vessels.

Results

Sample was clear, colorless, and particle free upon dilution to 50 mL.

General Precaution

- a) This procedure is a reference point for sample digestion using a CEM system and may need to be modified or changed to obtain the required results on your sample.
- b) If using a vessel other than the recommended choice, adjust sample size and pressure limit to values appropriate for the vessel chosen.