

# Microwave Digestion of Paint - Latex Based

### **Procedure**

Weigh 1 g (0.5 g w/Xpress Vessels) of sample into the digestion vessel. Add 10 mL of HNO<sub>3</sub>. Gently swirl the mixture before closing the vessel.

#### **Notes**

HF is required for a total dissolution of inorganic filler if present.

If this procedure uses hydrofluoric acid. If it is necessary to complex the residual hydrofluoric acid or redissolve insoluble fluorides formed, an additional complexation step with boric acid should be used. This procedure can be found in the One Touch Method note entitled "Boric Acid HF Neutralization".

Recommended Equipment	Recommended Vessels	Reagents
MARS 6 MARS 6 iWave	EasyPrep EasyPrep Plus MARSXpress MARSXpress Plus	HNO <sub>3</sub>

Max Sample Weight	Sample Type	Control Type	Method Type
1 g	Organic	Ramp to Temperature	One Touch

Heating Progr	am					
Stage	Temp (°C)	*Ramp (mm:ss)	Hold (mm:ss)	Pressure (psi)	* Power (W)	Stirring
1	200	15:00	10:00	800	400-1800	Off

<sup>\*</sup> Ramp times and power may vary depending on the type and number of vessels.

## Results

Sample was clear, colorless, and particle free upon dilution to 50 mL.

#### **General Precaution**

- a) This procedure is a reference point for sample digestion using a CEM system and may need to be modified or changed to obtain the required results on your sample.
- b) If using a vessel other than the recommended choice, adjust sample size and pressure limit to values appropriate for the vessel chosen.
- c) The control / reference vessel must contain the largest and most reactive sample.
- d) Manual venting of CEM vessels should be performed when wearing hand/eye/body protection and when the vessel contents are at or below room temperature to avoid the potential for chemical burns. Always point the vent hole away from the operator.
- e) If programming as One Touch, the ramp time and power will be automatically determined based on the number and type of vessels detected.