

MARS 6TM Method Note

Microwave Digestion of Rubber (Synthetic)

Procedure

Weigh 0.25 g of the sample into the digestion vessel. Add 10 mL of HNO₃. Gently swirl the mixture and wait approximately 15 minutes before closing the vessel.

Notes

Recommended Equipment	Recommended Vessels	Reagents
MARS 6 MARS 6 iWave	EasyPrep EasyPrep Plus	HNO ₃

Max Sample WeightSample TypeControl TypeMethod Type0.25 gOrganicRamp to TemperatureOne Touch

Heating Program						
Stage	Temp (°C)	*Ramp (mm:ss)	Hold (mm:ss)	Pressure (psi)	* Power (W)	Stirring
1	210	15:00	15:00	800	900-1050	Off

^{*} Ramp times and power may vary depending on the type and number of vessels.

Results

Sample was clear, colorless, and particle free upon dilution to 50 mL.

General Precaution

- a) This procedure is a reference point for sample digestion using a CEM system and may need to be modified or changed to obtain the required results on your sample.
- b) If using a vessel other than the recommended choice, adjust sample size and pressure limit to values appropriate for the vessel chosen.
- c) The control / reference vessel must contain the largest and most reactive sample.
- d) Manual venting of CEM vessels should be performed when wearing hand/eye/body protection and when the vessel contents are at or below room temperature to avoid the potential for chemical burns. Always point the vent hole away from the operator.
- e) If programming as One Touch, the ramp time and power will be automatically determined based on the number and type of vessels detected.