

Mars 6TM Method Note

Microwave Digestion of Wood

Procedure

Weigh 0.5 g of the sample into the digestion vessel. Add 10 mL of HNO₃. Gently swirl the mixture and wait approximately 15 minutes before closing the vessel.

Notes

The use of HF may be required to digest any silicates found in the sample.

Recommended EquipmentRecommended VesselsReagentsMARS 6EasyPrepHNO3

MARS 6 EasyPrep
MARS 6 iWave EasyPrep Plus
MARSXpress
MARSXpress Plus

Max Sample WeightSample TypeControl TypeMethod Type0.5 gOrganicRamp to TemperatureOne Touch

Heating Program						
Stage	Temp (°C)	*Ramp (mm:ss)	Hold (mm:ss)	Pressure (psi)	* Power (W)	Stirring
1	200	15:00	15:00	800	900-1050	Off

^{*} Ramp times and power may vary depending on the type and number of vessels.

Results

Sample was clear, colorless, and particle free upon dilution to 50 mL.

General Precaution

- a) This procedure is a reference point for sample digestion using a CEM system and may need to be modified or changed to obtain the required results on your sample.
- b) If using a vessel other than the recommended choice, adjust sample size and pressure limit to values appropriate for the vessel chosen.
- c) The control / reference vessel must contain the largest and most reactive sample.
- d) Manual venting of CEM vessels should be performed when wearing hand/eye/body protection and when the vessel contents are at or below room temperature to avoid the potential for chemical burns. Always point the vent hole away from the operator.
- e) If programming as One Touch, the ramp time and power will be automatically determined based on the number and type of vessels detected.